

*Cite as Jt.  
Text not analyzed*

[First Hit](#)      [Previous Doc](#)      [Next Doc](#)      [Go to Doc#](#)

☐ [Generate Collection](#)      [Print](#)

L9: Entry 13 of 14

File: DWPI

Nov 7, 1980

DERWENT-ACC-NO: 1981-53172D

DERWENT-WEEK: 198129

COPYRIGHT 2005 DERWENT INFORMATION LTD

TITLE: Binder for heat resistant concrete mfr. - contains Portland cement and finely finely milled ferroboron slag to increase strength after firing

INVENTOR: LUNEV, A A; SHTEPAN, G E ; VASILEVA, G M

PRIORITY-DATA: 1978SU-2671152 (July 24, 1978)

[Search Selected](#)      [Search ALL](#)      [Clear](#)

## PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAIN-IPC
<input type="checkbox"/> <u>SU 776999 B</u>	November 7, 1980		000	

INT-CL (IPC): C04B 7/14

ABSTRACTED-PUB-NO: SU 776999B

## BASIC-ABSTRACT:

Portland cement binder (e.g. for heat proof cement and plaster and heat-insulating material prepn.) contains finely-milled ferroboron slag to increase strength after firing. The proposed compsn. is (in wt.%): Portland cement 30-60; ferroboron slag (of compsn. (wt.%): SiO<sub>2</sub> 2.08; Al<sub>2</sub>O<sub>3</sub> 66.65; CaO 14; MgO 12.8; FeO 2; B<sub>2</sub>O<sub>3</sub> 4.34) 40-70.

The proposed slag (having high Al<sub>2</sub>O<sub>3</sub> content and absence of low fusion B<sub>2</sub>O) gives high refractory properties (over 1450 deg.C) and heat resistance.

[Previous Doc](#)      [Next Doc](#)      [Go to Doc#](#)